CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Date: 15-07-19

Lab ID	:	**CP-2019-11-12-14**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-07-19
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 . 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11).1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	13-07-19
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.55	–
2	Finess by Air permeablity method (m^2/kg,Min)	287.5	225m^2/kg, Min
3	Density (gm/cc)	3.11	–
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	145 minutes	Not less than 30 minutes
6	Final Setting time	280 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	2.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2019-11-12-14** **Date: 10-08-19**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-07-19
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	13-07-19
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	29.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	40.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	57.5N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2019-11-12-14** **Date: 15-07-19**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	12-07-19
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	12-07-19

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80mm	0	0	0.0	100	100
2	40 mm	420	420	2.8	97.2	90-100
3	20 mm	5863	6283	41.9	58.1	30-70
4	10 mm	4222	10505	70.0	30.0	10-35
5	4.75 mm	4227	14732	98.2	1.8	0-5
6	Pan	268	15000	100.0	0	—

CIVIL PRO Sig. Date

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2019-11-12-14** **Date: 15-07-19**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	12.4	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.3	
3	Specific Gravity	2.65	–
4	Bulk Density(Loose) (Kg/l)	1.55	–
5	Bulk Density(Compacted) (Kg/l)	1.6	–
6	Water Absorption(%)	0.22	–

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig. Date. BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Date: 15-07-19

Lab ID	:	CP-2019-11-12-14
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-07-19
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	12-07-19

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	250	250	5.0	95.0	90-100
3	10 mm	2789	3039	60.8	39.2	25-55
4	4.75 mm	1550	4589	91.8	8.2	0-10
5	Pan	411	5000	100	0	–

CIVIL PRO Sig. Date BANGALORE

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2019-11-12-14** **Date: 15-07-19**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.2	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.4	
3	Specific Gravity	2.65	–
4	Bulk Density(Loose) (Kg/l)	1.53	–
5	Bulk Density(Compacted) (Kg/l)	1.55	–
6	Water Absorption(%)	0.22	–
7	Aggregate crushing Value(%)	24.1	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	23.8	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

End of Report

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Date: 15-07-19

Lab ID	:	**CP-2019-11-12-14**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-07-19
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	12-07-19
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	28	28	2.8	97.2	90-100	90-100	90-100	95-100
3	2.36 mm	53	81	8.1	91.9	60-95	75-100	85-100	95-100
4	1.18 mm	241	322	32.2	67.8	30-70	55-90	75-100	90-100
5	600 micron	207	529	52.9	47.1	15-34	35-59	60-79	80-100
6	300 micron	201	730	73.0	27.0	5-20	8-30	12-40	15-50
7	150 micron	190	920	92.0	8.0	0-10	0-10	0-10	0-15
8	Pan	80	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL PRO Sig. Date. BANGALORE

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2019-11-12-14** **Date: 15-07-19**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.8	–
2	Specific Gravity	2.6	–
3	Material finer than 75 micron(%)	6.7	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig. Date. BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID	:	**CP-2019-11-12-14** **Date: 17-07-19**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	16-07-19
Sample Type	:	Sunvik
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.
Date of test:	:	16-07-19

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.391	512	652	20.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.616	528	672	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.888	544	668	20.0%	Satisfactory	Satisfactory

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig Date BANG

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 26/07/2019

Lab ID	:	CP-2019-11-12-14
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No 05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	22-07-19
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	26/07/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	19/07/2019	26/07/2019	150.74 X 149.31 X 151.50	22507	8.424	425.7	18.9	18.9
2	Drain Bottom Slab Concrete	M20	19/07/2019	26/07/2019	150.57 X 150.78 X 150.00	22704	8.435	427.7	18.8	
3	Drain Bottom Slab Concrete	M20	19/07/2019	26/07/2019	150.92 X 149.16 X 150.82	22511	8.251	425.7	18.9	

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig. Date BANG

Page 1/1
****End of Report****

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 16/08/2019

Lab ID	:	CP-2019-11-12-14
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	22-07-19
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/08/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	19/07/2019	16/08/2019	151.15 X 149.66 X 150.45	22620	8.978	542.3	24.0	23.4
2	Drain Bottom Slab Concrete	M20	19/07/2019	16/08/2019	151.71 X 150.89 X 149.01	22892	8.219	512.9	22.4	
3	Drain Bottom Slab Concrete	M20	19/07/2019	16/08/2019	151.54 X 150.68 X 151.73	22835	8.867	543.1	23.8	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig. Date BANG

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

Name of Work: [illegible]

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No. CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 26/07/2019

Lab ID	:	CP-2019-11-12-14
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	22-07-19
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	26/07/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	19/07/2019	26/07/2019	151.80 X 149.20 X 149.09	22648	8.424	411.3	18.2	18.3
2	Drain Bottom Slab Concrete	M20	19/07/2019	26/07/2019	150.78 X 150.48 X 150.22	22690	8.435	427.7	18.8	
3	Drain Bottom Slab Concrete	M20	19/07/2019	26/07/2019	149.14 X 150.42 X 150.58	22434	8.251	404.2	18.0	

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 16/08/2019

Lab ID	:	CP-2019-11-12-14
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	22-07-19
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	16/08/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	19/07/2019	16/08/2019	149.84 X 150.04 X 150.87	22481	8.978	532.1	23.7	23.4
2	Drain Bottom Slab Concrete	M20	19/07/2019	16/08/2019	150.90 X 149.85 X 150.31	22612	8.219	514.6	22.8	
3	Drain Bottom Slab Concrete	M20	19/07/2019	16/08/2019	150.76 X 151.78 X 150.92	22882	8.867	542.0	23.7	

Note:
1. The results pertain to the samples received and tested.
2. All information furnished by Customer/Representative
3. Any correction in the report will make this report invalid
4. This report without prior written approval should not be reproduced or published in full or part.
5. Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 31/07/2019

Lab ID	:	CP-2019-11-12-14
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	26-07-19
Customer ID	:	Drain Side wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/07/2019

SL No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side wall Concrete	M20	24/07/2019	31/07/2019	149.18 X 150.32 X 151.24	22425	8.424	421.1	18.8	18.7
2	Drain Side wall Concrete	M20	24/07/2019	31/07/2019	150.27 X 151.61 X 150.75	22782	8.435	418.6	18.4	
3	Drain Side wall Concrete	M20	24/07/2019	31/07/2019	151.40 X 149.43 X 149.71	22624	8.251	425.4	18.8	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TT/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 21/08/2019

Lab ID	:	CP-2019-11-12-14
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No 05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	26-07-19
Customer ID	:	Drain Side wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	21/08/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side wall Concrete	M20	24/07/2019	21/08/2019	150.88 X 149.20 X 149.11	22510	8.978	529.6	23.5	23.2
2	Drain Side wall Concrete	M20	24/07/2019	21/08/2019	151.63 X 150.12 X 150.26	22763	8.219	522.0	22.9	
3	Drain Side wall Concrete	M20	24/07/2019	21/08/2019	150.87 X 149.14 X 149.09	22501	8.867	522.2	23.2	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE
Sig.
Date.

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 31/07/2019

Lab ID	:	CP-2019-11-12-14
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	26-07-19
Customer ID	:	Drain Side wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	31/07/2019

SL No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side wall Concrete	M20	24/07/2019	31/07/2019	150.41 X 150.11 X 149.25	22579	8.424	413.1	18.3	18.5
2	Drain Side wall Concrete	M20	24/07/2019	31/07/2019	149.01 X 151.43 X 149.87	22565	8.435	423.0	18.7	
3	Drain Side wall Concrete	M20	24/07/2019	31/07/2019	151.69 X 150.03 X 151.92	22757	8.251	417.6	18.4	

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 21/08/2019

Lab ID	:	CP-2019-11-12-14
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Emergency Works Likes JCB Tractor Labour Debrit Clearance Should Drains Cluverts and Other Works in Ward No.05 Sourrounding Area Byatarayanapura Sub Division.
Agency	:	M/s Shree Charan Constructions, Prop. Sri T.S Kothandaraju, No. 05, Sree Sri nivas, Bagath Enclave, Kattegenahalli Yelahanka, Bangalore-560064.
Customer's Reference	:	BBMP/EE/BTP/WO/55/2019-20
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	26-07-19
Customer ID	:	Drain Side wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	21/08/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side wall Concrete	M20	24/07/2019	21/08/2019	150.44 X 150.61 X 149.54	22658	8.978	541.3	23.9	23.4
2	Drain Side wall Concrete	M20	24/07/2019	21/08/2019	151.88 X 151.74 X 149.94	23046	8.219	526.0	22.8	
3	Drain Side wall Concrete	M20	24/07/2019	21/08/2019	150.90 X 151.60 X 150.84	22876	8.867	533.9	23.3	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಅಭಿಯಂತರರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned by CamScanner